

Data Sheet

Eco Type 1

Limestone aggregate perfect for projects requiring a strong sub-base

Recycled from a Somerset located quarry, expert quality controlled MOT.

MOT Type 1 granular sub-base, suitable for roadways, footpaths, driveways and patios. Our aggregate is a blend of crushed limestone, ranging from 40mm to dust.

The mixture of stone and fines compacts down to ensure minimal voids in any project, providing a strong and durable sub-base.

Limestone used in the Eco Type 1 Aggregate is sourced directly from the Whatley Quarry in the Mendips, Somerset.



13 Sieves: Aperture/diameter	Specified % passing Min-Max
63 / 300mm	100-100
31.5 / 300mm	75-99
20 / 300mm	Spacer
16 / 300mm	43-73
14 / 300mm	Spacer
10 / 300mm	Spacer
8 / 300mm	23-53
6 / 300mm	Spacer
4 / 300mm	12-42
2 / 300mm	6-32
1 / 300mm	3-23
500µm / 300mm	Spacer
63µm / 300mm	0-9

User Benefits

- Provides the best foundation for landscaping projects and more
- Easy to apply
- Requires little maintenance
- Compacts down to reduce voids and gaps

Restrictions

Not suitable for use as a top layer for gardens and aesthetic-inspired locations.